

MATERIAL DATA SHEET

ECORUBBER 3 (black)

Ethylene-Propylene-Rubber (EPDM)

peroxide-cured

marked with blue dye

DIN/ISO

EPDM

ASTM

EPM

Property	Unit	Value	Standard
Durometer hardness	SHORE A	85 ± 5	DIN 53505
Density	g/cm ³	$1,22 \pm 0,02$	DIN 53479
Tensile strength	N/mm ²	≥ 12	DIN 53504
Elongation at break	%	≥ 110	DIN 53504
100 % modulus	N/mm ²	≥ 9	DIN 53504
Compression set: 100°C / 22h	%	≤ 15	DIN ISO 815
Tear strength	N/mm	15	DIN 53515
Rebound resilience	%	38	DIN 53512
Abrasión	mm ³	120	DIN 53516
Minimum service temperature	°C	-50	----
Maximum service temperature	°C	+150	----
Heat resistance, air 70h/150°C: Change in durometer hardness Change in tensile strength Change in elongation at break	Shore A % %	+4 -15 -22	DIN 53505 DIN 53504 DIN 53504
Compatibility with SL-DOT 4 - 168h/100°C Change in durometer hardness Volume change	Shore A %	0/-1 +2,1	DIN 53505 DIN 53521

The mentioned data are only valid for test pieces of the corresponding ISO, DIN and ASTM standards and cannot be directly related to gaskets and joints. The values which are marked with the symbols greater than (\geq) and smaller than (\leq) are nominal values and must be fulfilled of each batch. All values which are not marked are typical values which are only tested on selected samples.

Valid from the manufacturing date week 45/1998

Judenburg, November 1998
Dr. TS/He wdrub3e/werkstoffe