

# Technical Data Sheet

## MyPrint Gloss

### High Gloss Water Based Ink Series

#### Main Characteristics

- Very high gloss
- Good printability and re-solubility
- Excellent rub resistance
- Fast drying
- High color strength

#### Printing Techniques

- Flexography

#### Printing Substrates

- Coated paper
- Uncoated paper

#### Viscosities (Din 4 at 25°C.)

- Printing viscosity  
18-22 sec
- Production viscosity  
30-45 sec

#### Grinding

- 5-10 microns measured  
with Hegman grindometer

#### pH

- 8.5-9.5
- After long storage, please check the pH level of the ink and use our pH modifier when needed.

#### Dilution

- 10% water

#### Storage


- Store in a covered and ventilated area
- Max 12 Months


#### Available Additives

- Diluting varnish
- Retarder
- Refresher
- Anti-foam
- Leveling agent
- Cleaning solution

For further information  
please contact us:

**Chemiprint.**  
**23 Hamasger st.**  
**Bet-Shemesh, Israel**  
**99060**

 Phone: +972-2-9901888

 Fax: +972-2-9901899

 E-mail: [info@chemiprint.co.il](mailto:info@chemiprint.co.il)

 Website: [www.chemiprint.com](http://www.chemiprint.com)

**chemiprint**  
ImagineINK.